



INTRODUCING . . .

FORMWOOD® PRESSURE-SENSITIVE ADHESIVE (PSA) VENEER

FormWood PSA veneer provides a simple and easy alternative for applying veneer without the need to use a secondary adhesive.

Utilizing the best quality 3M™ Brand PSA adhesives, our peel & stick veneer provides a permanent bond to any smooth substrate that is dry and free of dust and contaminants.



FEATURES AND BENEFITS

- Partnered with the quality of the 3M™ peel & stick adhesive backing, our PSA veneer is backed to provide excellent flexibility
- PSA-backed veneer is the perfect choice for cabinet refacing, home craftsmen and professional woodworkers
- Sheet sizes are 2' x 8', 2' x 10', 4' x 8' and 4' x 10'
- PSA veneer can be cut and trimmed with ordinary tools, such as scissors or a utility knife
- Common applications include: Kitchen Renovation, Furniture Repair, Column Wraps, Display and Fixture, Interior Architectural Design and Renovation
- 90-plus wood species and cuts, including many exotics on the shelf and ready for quick shipment
- Tenderized FormWood PSA veneer will bend to a tight radius
- Ships easily by UPS or FedEx

As with all FormWood products, the meticulous grading and matching of our veneer along with a station to station quality check system assures the end-user will get the same quality on every order.

The unmatched performance of our PSA veneer is a direct result of using superior materials and a team of dedicated veneer craftsmen.



FormWood Industries, Inc.
1601 Production Drive
Jeffersonville, IN 47130

Phone: (812) 284-3676
Fax: (812) 285-5074
www.FormWood.com
Email: info@formwood.com

FORMWOOD®
**PRESSURE-SENSITIVE
ADHESIVE (PSA)**
VENEER

Technical Specifications

Information provided is based on 4'x8' sheet

THICKNESS	.025" plus or minus .005"
MACHINE SURFACE SAND	150 grit
PACKAGING STANDARD	2-10 pcs / 11-15 pcs
TYPICAL BOX SIZE	11-3/8" x 11-3/8" x 50" / 13-5/8" x 13-5/8" x 50"
WEIGHT/4X8 SHEETS	4.4 lbs
(Bending Radius) FLEXIBILITY	1" (varies with species)
STANDARD SIZE	2' x 8'
MAXIMUM SIZE	4' x 10'

Storage:

- Best to store in a climate-controlled environment
(Heated in winter/Air-conditioned in summer)
- Relative humidity of 35% is best
- Avoid exposure to sunlight

Color and Grain Appearance:

- Variation can be expected from sheet to sheet and lot to lot
- Sequence matching available upon request

General Application Information:

- Inspect material for satisfaction of quality and grade prior to lamination
- All veneer should be acclimated prior to application
- Ideal temperature for application is 70-80° F
- Ideal humidity is 35%
- Surface must be clean, dry and smooth (free of dust, grease, wax)
to ensure a good bond
- Veneer scrapers are recommended for hand application to allow
for maximum pressure. "J" rollers are not recommended
- Adhesive should be allowed to cure for 48 hours prior to finishing
- Visit www.FormWood.com for detailed application instructions

FormWood Industries, Inc.
1601 Production Drive
Jeffersonville, IN 47130

Phone: (812) 284-3676
Fax: (812) 285-5074
www.FormWood.com
Email: info@formwood.com

