

JOWATHERM

Edgebanding Hot Melt

282.20

Basis:	Ethylene - Vinyl Acetate (EVA)
Technical Data:	Viscosity (mPas/cPs): approx. 60,000 at 130°C (266°F) Brookfield-Thermosel approx. 40,000 at 140°C (284°F) approx. 30,000 at 150°C (302°F) Density (g/ml): approx. 1.3 (10.8 lbs./gal) Softening Point: approx. 90°C (194°F) Ring & Ball Color: 20-natural; 21-white
Characteristics:	Low viscosity hot melt with fast melting properties, long open time and good color and heat stability in the melt.
Applications:	Designed for contour edgebanding of PVC, paper, and polyester at low application temperatures and at very slow feed speeds. Also suitable for softforming PVC edges.
Directions for use:	Application Temp: 130-150°C (266-302°F) in the melt Feed Speed: roller application: 5-20 m/min (15-60 ft/min) The structure of the edge material and working conditions may influence the bond. Tested according to Jowat test methods. Customer trials are recommended.
Cleaning:	Preliminary cleaning while hot by scraping with a spatula.
Storage:	At least 3 years from the date of manufacture in dry and cool (15-25°C/58-76°F) conditions according to our experience.
Packaging:	In plastic bags of 55 lbs. net.
Marking:	None. We recommend drawing off any vapors which may form. Consult Material Safety Data Sheet.
Date Revised:	September 2006 (S)

The information contained in this leaflet is based upon our practical experience and the results of tests in our laboratory. The information contained represents average values under our test conditions. Although our testing is constantly being revised to represent the latest conditions, the information provided in this leaflet and by our free technical information service should be used only as a guide, but cannot be relied upon as a guaranty of performance or results. We strongly recommend that any user of our products conduct its own testing.

SEE THE BACK OF THIS PAGE FOR ADDITIONAL IMPORTANT INFORMATION.



Jowat Corporation
Randolph Industrial Park
P.O. Box 1368
High Point, NC 27261
Phone: (800) 322-GLUE (4583)
(336) 434-9000
Fax: (336) 434-9019
Website: www.jowat.com
Email: info@jowat.com